

Proyecto Arqueologico Pedro Gonzalez, Archipelago Las Perlas

Analysis type	Analysis Date d/m/y	Analysis Operator	Name	R #	Analysis #	Fe	Cu	Ag	Au	Location of Analysis	Analysis notes	Reliability	Elements removed	Spectrum Analysis
XRF	16/9/2009	ACH	Bead	PAPG-H9	PAPG_H9_x1	0.0	22.5	77.5		Centered over window	clean surface	good	none	R
XRF	16/9/2009	ACH	Bead - small gold colored	PAPG-H3	PAPG_H3_1_x1	0.0	14.9	85.1		Centered over window	clean surface	good	none	R
XRF	16/9/2009	ACH	Bead - larger copper colored	PAPG-H3	PAPG_H3_2_x1	46.9	6.9	46.2		Centered over window	clean surface	good	Ni	FPA
XRF	16/9/2009	ACH	Bead - smaller copper colored	PAPG-H3	PAPG_H3_3_x1	19.4	12.8	67.8		Centered over window	clean surface	good	none	R
XRF	16/9/2009	ACH	Bead	PAPG-H11	PAPG_H11_1x	42.4	7.5	50.2		Centered over window	clean surface	good	Ni, count rate set between 5000-5600	FPA, Count rate set between 5000-5600
XRF	16/9/2009	ACH	Bead	PAPG-no #	PAPG_unnumbered_x1	0.6	41.8	7.3	50.3	Centered over window	clean surface	good	Ar, Os, count rate set between 5000-5600	FPA, Count rate set between 5000-5600
XRF	16/9/2009	ACH	Bead	PAPG-H7	PAPG_H7_x1	3.7	13.2	83.2		Centered over window	clean	good	none	R
XRF	16/9/2009	ACH	Bead	PAPG-H10	PAPG_H10_x1	49.0	7.2	43.8		Centered over window	clean	good	Ni, count rate set between 3000-3600	FPA, Count rate set between 3000-3600